

Indorama Eleme Petrochemicals Limited**TECHNICAL DATA SHEET****INDORAMA – HDPE****HEG00952**

HIGH DENSITY PE GRADE FOR RAFFIA / TAPES APPLICATION

HEG00952 High Density Polyethylene Resin manufactured by IEPL using "SCLAIRTECH" solution polymerisation process of DU Pont, Canada (Now Nova Chemicals) offers medium molecular weight material with broad molecular weight distribution. As a copolymer it combines excellent orientation characteristic, negligible water carry-over, low gel/fisheyes content with excellent balance of high tenacity and good elongation, therefore specially suitable for making raffia tapes & monofilament. It can be easily processed on norm raffia tape plant using processing temperatures between 190 and 230 °C.

TYPICAL CHARACTERISTICS:

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	gm/10 min.	0.9
Density	ASTM D 792	gm/cm ³	0.952
Tensile Strength at Yield (MD/TD)	ASTM D 882	Mpa	34.5 / 37.5
Ultimate Tensile Strength (MD/TD)	ASTM D 882	Mpa	50 / 45
Elongation at Break (MD/TD)	ASTM D 882	%	900 / 950
Dart Impact Test. F ₅₀	ASTM D 1709	g/μm	1.5
Tear Strength (MD/TD)	ASTM D 1922	g/μm	0.6 / 1.7

Above values are not to be construed as specifications.

PRODUCT BENEFITS

- Excellent orientation characteristics
- Good processability
- Low gels / fish eyes
- High tenacity & good elongation

APPLICATIONS

- Woven sacks
- Monofilament for ropes
- Oriented tapes
- Jumbo bags
- Tarpaulins

PACKAGING: HEG00952 is available in natural colour, pallets form in 25 Kg bags.

FOOD CONTACT APPLICATIONS:

This grade meets with the requirements of FDA: CFR title 21, 177.1520 and EC regulation 2002/72/EC for food contact application when used unmodified and processed according to good manufacturing practices. Please contact us for details information and/or compliance certification documents.

The data, information and suggestions given herein are purely as a guide. IEPL undertakes no responsibility either for the results derived from their adoption or for possible positions in apparent contrast with existing patent rights.

Indorama Eleme Petrochemicals Limited**TECHNICAL DATA SHEET****SAFETY**

The Material Safety Data Sheet (MSDS) contains information regarding health, safety and waste considerations for all IEPL High Density Polyethylene grades. We urge each customer or recipient of MSDS to study it carefully to become aware of and understand the hazards associated with the product. The customer should consider consulting reference works or individuals who are experts in ventilation, toxicology or fire prevention, as necessary or appropriate to use and understand the data contained in the MSDS.

STORAGE

The material is packed in 25 kg bags protecting it from contamination. Storage times of natural materials longer than 6 months may have a negative influence on the quality of the final product. It is generally recommended to convert all material latest within 6 months of production. The material is subjected to degradation by ultra-violet radiation or by high storage temperatures. Therefore the material must be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Further unfavorable storage conditions are large fluctuations in ambient temperature and high atmospheric humidity. These conditions may lead to moisture condensing inside the packaging. Under these circumstances, it is recommended to dry the material before use. After a storage period of more than 3 months drying of such material is recommended as standard practice.

DISCLAIMER

"The information in this publication is submitted without prejudice, and is based on our current knowledge and experience and on a limited number of tests." In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication.

OFFICES:**Export Sales**

Chirag Jesalpura
Mobile: +2348052307986
E-mail: export@indorama.com.ng

Customer Services

Krishan Kant Verma
Mobile: +2348129124582
E-mail: techsupport@indorama.com.ng

Lagos

12th Floor, Zenon House,
Ajose Adeogun Street,
Victoria Island, Lagos
E-mail: lgsales@indorama.com.ng
+2348055200738

Port Harcourt

IEPL Complex,
PMB 5151, Port Harcourt,
Rivers State
E-mail: phcsales@indorama.com.ng
+2348057700089

Kano

No. 6, Niger Street,
Dakata
Kano
E-mail: kanosales@indorama.com.ng
+2348056009023

www.indoramaeleme.com

The data, information and suggestions given herein are purely as a guide. IEPL undertakes no responsibility either for the results derived from their adoption or for possible positions in apparent contrast with existing patent rights.